



QUICK TARP LABORATOY TEST RESULTS

Property	Test Method	Results					
		English Units		SI Units			
		MD	TD		MD	TD	
Mass/Unit Area	ASTM D 5261	9.27		oz/sq yd	219.73		g/sq m
Grab Tensile Strength	ASTM D 4632	642	422	lbs	2855	1877	N
Grab Tensile Elongation	ASTM D 4632	17	18	%	17	18	%
Wide Width Tensile Ultimate	ASTM D 4595	3394	1708	lbs	15101	7599	N
Wide Width Elongation	ASTM D 4595	10.2	13	%	10.2	13	%
Trapezoidal Tear	ASTM D 4533	271	158	lbs	1205	703	N
CBR Puncture Strength	ASTM D 6241	1468		lbs	6530		N
Permittivity	ASTM D 4491	No Flow		GPM/sq ft	No Flow		LPM/sq m
Thickness	ASTM D 4491	27		mils	0.69		mm
Apparent Opening Size ⁽¹⁾	ASTM D 4751	2.95		mils	0.075		mm
UV Resistance ⁽²⁾	ASTM D 4355	93.75 ⁽³⁾		%	93.75 ⁽³⁾		%
Flammability	ASTM E 84	Class A			Class A		

Notes:

- MD - Machine Direction
- TD - Transverse Direction
- (1) - Using 200 Sieve
- (2) - 1200 hours
- (3) - Average

